## **DATA SHEET**

## **DRENFOL 500+110**

## geocomposite

**DRENFOL 500+110 geocomposite**, the height of dimples is about 8 mm, HDPE membrane thickness of about 0,5 mm, geotextile PE, product type F+S+D (filtration, separation, drainage) according to the harmonized standard EN 13252

product type 1 370 (Intration, Separation, dramage) according to the narmonized standard EN 13232			
Property	Test Method	Unit	Value
Tensile strength	PN EN ISO 10319	kN/m	MD 15 (-1,5)
			CMD 15 (-1,5)
Relative elongation at maximum load	PN EN ISO 10319	%	MD 45 (±5,6)
			CMD 38 (±2,6)
In-plane water flow capacity of a product 20kPa gradient 1,0	PN EN ISO 12958	I/(ms)	3,2 (-0,24)
Resistance to static puncture (CBR)	PN EN ISO 12236	kN	1,00 (-0,10)
Dynamic perforation resistance (cone drop)	PN EN 13433	mm	35 (+7)
Characteristic opening size	PN EN ISO 12956	μm	140 (± 42)
Water permeability normal to the plane of a product V <sub>H50</sub>	EN ISO 11058	m/s	70x10 <sup>-3</sup> (-21x10 <sup>-3</sup> )
Durability (According to Annex B) resistance to weathering against ageing	PN EN 12224	-	Cover within 2 weeks after application
Durability (According to Annex B) resistance to chemical degradation	PN EN ISO 13438	-	Durability planned for a minimum of 25 years on natural soils with a 4 <ph<9 and a temperature &lt;25°C</ph<9 
Mass per unit area	PN EN ISO 9864: 2007	g/m²	640 (±65)
Compressive strength	PMS 967252: 2013	kN/m²	225 (-21)
Joint - seam*	Туре	Mechanical modular seam (overlap), approx. 200 mm - Strengthened version: joined sheets additionally glued within the seam area with a double sided adhesive tape - Sealed version: at least 5 mm butyl tape within the seam area	

The table contains average values of each property from tests made during the period from September 2013 until March 2014.



<sup>\*</sup> The joint made during installation by a contractor.